

Site preparation

The temperature of the wall may alter the reaction time of Everseal Flex Foam when it is injected. Colder walls and concrete will extend the reaction time. Warmer walls will shorten the reaction time. The reaction can be accelerated by heating Everseal Flex Foam. Our recommended application temperature is between 55°F to 90°F (12.8°C to 32.2°C).

Precautions

This material is intended to be used by trained professionals with the proper equipment. The following safety measures are recommended:

- Wear protective gloves, clothing, goggles, hearing protection for noise reduction and hard hats for falling debris.
- Do not eat, drink or smoke while in active contact with these materials.
- Avoid skin contact.
- Wash hands thoroughly with soap and cool water. Never wash the skin with a solvent.
- Anyone experiencing difficulty breathing when working with these materials or showing an allergic reaction should seek fresh air immediately and consult a physician if symptoms persist.

Depending on the scope of the project, it may be advisable to consult a manufacturer's representative during installation.

Material storage

Container should be stored above 60°F (15°C) and below 120°F (48°C).

All spills of Everseal Flex Foam should be disposed by absorbing the grout into an inert material and then transferring the mixture to an open top drum. Do not seal the waste drums for 24 hours to allow the Everseal Flex Foam to react completely. Dispose of waste material in accordance with state and local regulations.

Warranty

CME warrants this product from one year of date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

WARRANTY The information contained in this document is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. The customer must inspect and test our products before use, and satisfy themselves as to the contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials, and in no event shall we be liable for special, incidental or consequential damages.