

Everseal Surface Paste and Port Adhesive

Product description

Everseal Surface Paste is an epoxy specifically designed to adhere plastic surface ports to concrete for concrete crack injection. These components react quickly at room temperature to form an epoxy that is stronger than many of the bonded substrates.

- Designed to adhere ports and seal concrete cracks
- Best dispensed on a pallet and spread with a trowel
- Works well in situations requiring speed and strength

Properties

- 4-5 minute initial set
- Strong bond typically stronger than the substrate
- 30 minutes ready for injecting
- Low odor

Table 1: Physical properties of uncured materials

PROPERTIES	PART A	PART B	MIXED
Solids by Volume	100%	100%	_____
Color	White	Black	Grey
Shelf Life	1 year	1 year	-----
Weight by Gallon	9.9 - 10.1 lbs	9.9 - 10.1 lbs	9.9 - 10.1 lbs
Mix Ratio (Vol)	-----	-----	1:1
Pot Life: (3 oz)	-----	-----	10-20 minutes
Gel Time (5 mil)	-----	-----	30 minutes
Final Cure	-----	-----	7 days
Viscosity	-----	-----	Non sag gel
Hardness (Shore)	-----	-----	80-D
Ultimate Pull Out Strength	-----	-----	14,000 lbs (Concrete Failure)

Everseal Surface Paste and Port Adhesive

Curing Physical Properties

Gel Time	4-5 minutes
Trixtropy	8-10 minutes
Injection Ready	30 minutes
Full Cure	24 Hours

Disclaimer of Warranty

All statements, technical information and recommendations herein are based on tests believed to be reliable. BUT THE ACCURACY OR COMPLETENESS THEREOF IS NOT GUARANTEED AND THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PURPOSE. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therein. NEITHER SELLER NO MANUFACTURER SHALL BE LIABLE EITHER IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, ARISING OUT OF THE USE AND OR THE INABILITY TO USE THE PRODUCT. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.